

DEPARTMENT OF TRADE AND INDUSTRY  
DEPARTEMENT VAN HANDEL EN NYWERHEID

REPUBLIC OF SOUTH AFRICA



REPUBLIC VAN SUID-AFRIKA

LETTERS PATENT  
(PATENTS ACT, 1978)

PATENTBRIEF  
(WET OP PATENTE, 1978)

No. 88/6259

WHEREAS ~~NADEMAAL~~ FIBERLOK INC. *Substituted by High Voltage Graphics Inc (8 April 1991)*  
(Hereinafter called "the Patentee")  
(Hieronder "die Patenthouer" genoem)

has applied to me for the grant of a patent in respect of an invention described and claimed in the complete specification deposited at the  
aansoek by my gedoen het om die verlening van 'n patent ten opsigte van 'n uitvinding wat beskryf is en waarop aanspraak gemaak word

Patent Office under the above-mentioned number, a copy of which is annexed, together with the relevant Form P. 2;  
in die volledige spesifikasie wat by die Patentkantoor onder bovermelde nommer ingedien is en waarvan 'n afskrif aangeheg is tesame met  
die betrokke vorm P. 2;

NOW THEREFORE these Letters Patent are to grant to the Patentee a patent, the effect of which shall be to grant to the Patentee  
SO IS DIT dat hierdie Patentbrief aan die Patenthouer 'n patent verleen wat die uitwerking het dat, behoudens die bepalings van die  
in the Republic, subject to the provisions of the Act, for the duration of the patent, the right to exclude other persons from making, using,  
Wet, aan die Patenthouer vir die duur van die patent in die Republiek die reg verleen word om ander persone uit te sluit van die vervaar-  
exercising or disposing of the invention, so that he shall have and enjoy the whole profit and advantage accruing by reason of the invention.  
diging, aanwending, uitoefening of van die handsetting van die uitvinding, sodat hy al die wins en voordeel wat uit die uitvinding voort-  
spruit, verkry en geniet.

IN TESTIMONY WHEREOF the seal of the Patent Office has been affixed at Pretoria with effect from the  
TER BETUIGING WAARVAN die seël van die Patentkantoor hierop te Pretoria aangebring is met ingang van die

25TH

day of  
dag van APRIL

nineteen hundred and  
eenduisend negehonderd NINETY

Registrar of Patents/Registrateur van Patente

[See overleaf  
[Blaai om



# PATENT

1. The patent remains in force only if the required renewal fees are paid annually after the third year of the date of application.  
Die patent is geldig slegs indien die vereiste hernuwingsgelde jaarliks, na die derde jaar vanaf die datum van aansoek betaal word.
2. This document is not valid unless sealed with the seal of the Patent Office, PRETORIA.  
Hierdie dokument is nie geldig nie tensy geseël met die seël van die Patentkantoor, PRETORIA.

B.P.S. 019-0194

H.S.

REPUBLIC OF SOUTH AFRICA

Official application

21 01 88

International class

51 B32B, B32C

Full name(s) of applicant

71 [REDACTED]

Applicants subsidiary

71 [REDACTED]

Assignee(s):

71 [REDACTED]

Full name(s)

72 (1)  
(2)

Prior art

Title of invention

54 [REDACTED]

Address

[REDACTED]

Address

74 [REDACTED]

Patent

61 [REDACTED]

Fresh

REPUBLIC OF SOUTH AFRICA

## REGISTER OF PATENTS

PATENTS ACT, 1978

H 573

Official application No.		Lodging date: Provisional		Acceptance date	
21	01	886259		22	
International classification		Lodging date: Complete		Granted date	
51	B32B, B44C		23	1988-08-24	
Full name(s) of applicant(s)/Patentee(s)		1990-04-25			
71	[REDACTED] FIBERLOK INC. Substituted by High Voltage Graphics Inc (8 April 1991)				
Applicants substituted:				Date registered	
71					
Assignee(s):				Date registered	
71					
Full name(s) of inventor(s):					
72	(1) LOUIS BROWN ABRAMS (2) GERHARD ARZBERGER				
Priority claimed		Country		Number	
		33	U.S.	31	88,292
		33		31	
		33		31	
Title of invention:					
54	PLUSH TEXTURED MULTICOLOURED FLOCK TRANSFER AND METHOD FOR MAKING SAME USING PRECOLOURED FLOCK				
Address of applicant(s)/patentee(s)					
1520 Washington Avenue, St. Louis, Missouri 63166					
Address for service					
74	MACROBERT DE VILLIERS & HITGE INC. (D1/7813/001)				
Patent of addition No.		Date of any change			
61					
Fresh application based on		Date of any change			

lication.  
betaal word.

(To be lodged in duplicate)

REPUBLIC OF SOUTH AFRICA

PATENTS ACT, 1978

COMPLETE SPECIFICATION

[Section 30 (1)—Regulation 28]

Official application No.

21 01 88/6259

Lodging date

22 24 August 1988

International classification

51 B32B, B44C

Full name(s) of applicant(s)

71 FIBERLOK INC

Full name(s) of inventor(s)

72 LOUIS BROWN ABRAMS and GERHARD ARZBERGER

Title of invention

54 PLUSH/TEXTURED MULTICOLOURED FLOCK TRANSFER AND METHOD FOR MAKING SAME USING PRECOLOURED FLOCK

PLUSH TEXTURED MULTICOLORED FLOCK TRANSFER AND METHOD  
FOR MAKING SAME USING PRECOLORED FLOCK

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The invention generally relates to a method of manufacturing flock transfers. Specifically, the invention is directed to methods of manufacturing flock transfers which exhibit an enhanced texture, particularly flock transfers composed of a plurality of precolored flock.

10 2. Description of the Prior Art

There are two basic methods of applying a multicolor flock design to a surface. The first method is referred to as direct flocking. The second is by means of flock transfers.

15 In the former instance, the flock is applied directly to the surface that forms the finished product. Usually wallpaper, carpets and decorative elements of garments are produced in this manner.

An example of direct flocking is found in U.S. Patent  
20 No. 3,793,050 to Mumpower. This particular direct flocking method is unique in that it allows the use of different color and size of flock in the same design surface to be flocked. The adhesive is rendered tacky and each color of flock is passed through a screen that restricts that color  
25 to the desired part of the adhesive layer. A multicolor flock design is thus obtained on the surface.

Multicolor direct flocking suffers a number of disadvantages. It is an exacting procedure with many variables to be controlled requiring specialized flocking  
30 equipment and an environment that is controlled for relative humidity. During the startup of such a procedure many reject-quality articles may result as the variables are adjusted by trial and error until the desired result is found. The procedure is relatively slow since usually only  
35 one article at a time may be decorated. Further, if the article to be decorated has an uneven surface like many

textiles, then density of the flock, control, speed and the quality of the finished design i.e. sharpness of lines separating colors, vivid images, etc., would be adversely affected.

5       It is believed that direct flocking has been limited in use in the United States.

      Examples of flock transfers, i.e., the second method of employing flock fibers in a decorative manner, are illustrated in United States Patents 4,292,100 and 4,396,662  
10 both to Higashiguchi and UK Patent applications 2,065,031 to Maitland and 2,126,951 to Transworth. Transfers are formed by applying flock to a release sheet having a temporary release adhesive coating. The flock is then colored with different color inks and coated with a binding layer and hot  
15 melt adhesive in a desired decorative design. The transfers are applied to articles with heat and pressure. The release sheet is peeled away leaving a finished decorative design.

      Conventional multicolor flock transfers also suffer from a number of disadvantages. The basic underlying  
20 problem is that the flock transfers use a very short fiber and are, therefore, relatively flat so that a plush textured multicolored look is not achieved. Thus, a transfer having a richly textured appearance has not been achieved using flock to justify the additional cost over conventional  
25 screen printing.

      In this regard, flock fibers of conventional flock transfers must be short because of a fundamental limitation of conventional flock transfer manufacturing methods caused by the problem of penetrating the flock fiber with printing  
30 ink to form the desired design. Typical flock fibers used in flock transfers are only about 0.3 mm long because if fibers longer than about 0.3 mm are used, it is difficult for subsequently applied ink to penetrate along the full length of the fibers; when a sufficient amount of ink is  
35 supplied to do so there results a smudged design. This is unlike direct flocking which can use precolored flocks of

approximately 0.5 mm to 3 mm in length.

An object of the present invention, therefore, is to produce a plush textured multicolored flock transfer which has a three dimensional appearance using longer flock than  
5 heretofore was possible.

Another object is to provide a method of producing plush-textured, multicolored flock transfers in batches containing more than one transfer per batch.

Another further object of the invention is to provide a  
10 method of decorating articles with a multicolor plush textured design which overcomes the disadvantages and limitations of direct flocking.

Another still further object of the invention is to allow manufacturers of products to economically make use of  
15 plushly-textured flock designs in place of screen printed designs.

#### SUMMARY OF THE INVENTION

In general, the present invention is directed to a multicolored flock transfer comprising flock having a fiber  
20 length longer than about 3 mm, up to about 5 mm, and preferably longer than about 5 mm, up to about 1 cm, and longer than 1 cm for the most preferred plush texture.

Related to this, the present invention is also directed to a fabric including a substrate material; a layer of  
25 binding adhesive having a predetermined design applied to the substrate; and precolored flock of at least two different colors adhering to the layer.

In accordance with the present invention there is also provided a method of applying a multicolor flock transfer to  
30 a substrate material which involves providing a multicolor flock transfer including flock having a fiber length longer than about 3 mm up to about 5 mm, and preferably longer than 5 mm up to 1 cm, and more preferably longer than 1 cm, and applying the multicolor flock transfer using heat and  
35 pressure to a substrate material, such as a fabric or textile, which may have a textured or irregular surface.

In order to accomplish the previously mentioned objects, the present invention is directed to a method of making a multicolored flock transfer or transfer sheets which involves sequentially flocking a different precolored flock into a pre-designated color pattern of an overall design using flock having relatively long fibers to result in a plush textured flock transfer.

More particularly, the present invention is directed to a process for manufacturing transfer sheets which involves forming on the surface of a base sheet an adhesive layer for temporary adhesion of a plurality of different colored flock fibers to the base sheet, temporarily sticking the different colored flock to the adhesive layer to form a multicolored fiber layer, and applying an adhesive in the multicolor fiber layer to a desired pattern to form a binding adhesive layer, wherein the colored flock fibers are precolored to the plurality of different colors before sticking the different colored flock fibers to the adhesive layer.

The present invention, more specifically, is directed to a method of making a multicolored flock transfer which involves printing a release adhesive upon a base sheet; sequentially flocking different colored flock fibers through an open section of a barrier into the adhesive to result in a plurality of predetermined single color patterns arranged to form a predetermined design; and applying a binding adhesive to free ends of the flock fibers.

The present invention is also directed to a multicolor flock transfer which includes a base sheet having a surface area coated with a release adhesive; precolored flock fibers of at least two different colors having ends adhering to said surface area to form predetermined color patterns of a design; and a binding adhesive applied to other ends of said precolored flock fibers, wherein the multicolor flock transfer of the present invention preferably also includes a layer of supplemental adhesive covering the binding adhesive.



For purposes of the present invention, the colored flock include fibers longer than .3 mm, e.g., having a length within the range of 0.5-3 mm, but preferably having a length of at least about 3 mm up to about 5 mm, although  
5 fibers having a length greater than 5 mm up to about 1 cm are more preferred, and flock with fibers particularly longer than 1 cm are most preferred for producing flock transfers with a plush texture.

The flock fibers should be conductive material, such as  
10 synthetic materials, selected from the group consisting of rayon, nylon, polyamide and polyester materials, and preferably is rayon.

The base sheet is a material selected from the group consisting of paper, resin and metal foil and preferably is  
15 a dimensionally stable sheet of paper, which may be transparent.

The release adhesive may be applied in the form of a solution or emulsion, such as a resin or a copolymer, such as polyvinyl acetate, polyvinyl alcohol, polyvinyl chloride,  
20 polyvinyl butyral, acrylic resin, polyurethane, polyester, polyamides, cellulose derivatives, rubber derivatives, starch, casein, dextrin, gum arabic, carboxymethyl cellulose, rosin, or compositions containing two or more of these ingredients.

25 The binder adhesive is a resin, preferably selected from the group consisting of polyvinyl chloride, polyvinyl acetate, polyurethane, polyester polyamide, and acrylic resin, such as a water based acrylic resin, and may also include a hot melt adhesive, such as a hot melt adhesive  
30 selected from the group consisting of polyurethane, polyester and nylon, which is preferably applied as a separate adhesive layer.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is cross-section of the multicolor transfers in  
35 accordance with the present invention.

Fig. 2 is a cross-section of the multicolor transfer in

accordance with the present invention illustrated in Fig. 1 showing its application to a textile or fabric.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

As shown in Fig. 1, the transfer 2 of the flock transfer present invention comprises a base sheet 4, such as dimensionally stable paper, to which a conventional flock transfer release adhesive 6, usually silicone wax, is applied. The base sheet, however, may be any material which can be suitably used with the adhesive which should be selected to effect temporary adhesion of the flock fibers. Although paper, such as processed paper, is preferred, resin sheets and metal foils may also be employed. Depending on the desired effect and the sheet materials employed, the base sheet may be transparent, translucent or opaque.

The release adhesive 6 may be applied in the reverse of a desired pattern, that is, a pattern which corresponds to the overall image which is to be flocked. Preferably, however, the release adhesive may be applied without regard to the overall design desired, particularly when the precolored flocks are sequentially applied to the adhesives, as discussed in more detail hereinbelow. The release adhesive may be applied in the form of a solution or emulsion, such as a resin or a copolymer, such as polyvinyl acetate, polyvinyl alcohol, polyvinyl chloride, polyvinyl butyral, acrylic resin, polyurethane, polyester, polyamides, cellulose derivatives, rubber derivatives, starch, casein, dextrin, gum arabic, carboxymethyl cellulose, rosin, or compositions containing two or more of these ingredients.

The flock 8 is preferably composed of fibers, which may be referred to herein as flock fibers. The flock may be rayon, and other types of conductive material, such as nylon, polyamide, polyester and similar synthetic fibers, and is applied to the activated adhesive 6 by conventional electrostatic processes, spraying, or by gravity, such as sprinkling or vibrating the flock onto the surface of the base sheet provided with the release adhesive.

The flock 8 is coated with a binder adhesive 10, such as a water based acrylic, which binds the flock into a unit. Preferably the binding adhesive is applied in the form of a solution or emulsion. The binder adhesive preferably contains a resin, such as polyvinyl chloride, polyvinyl acetate, polyurethane, polyester, polyamide, and acrylic resin, and preferably the previously mentioned water based acrylic. The binder adhesive 10 may contain additional or supplemental adhesives, such as a hot melt adhesive, usually a granular polyester or nylon, for binding the transfer to a substrate. Alternatively, the hot melt adhesive 12, may form a separate layer. The use of separate hot melt layers is preferable. In addition, other heat sensitive adhesives, such as polyvinyl chloride, thermoplastic acrylic resin, polyethylene, polyamide, polyurethane, paraffin and rubber derivative may be used for this purpose, with polyurethane being preferred.

In order to achieve a multicolor effect, the flock 8 is applied through a barrier which is preferably a gauze-like mesh screen. The multicolor effect is achieved by using different precolored flock. As used herein, precolored flock means that the flock has been colored before being flocked, stuck or otherwise applied to the release adhesive. Depending on the overall design and the number of colors of flock which are to be used, an appropriate number of barriers or screens are prepared to have open sections to permit passage of flock in a predetermined configuration or color pattern. Alternatively, a single screen may be sequentially masked for this purpose. In either case, the open sections of each mask or screen are designed to permit passage of flock fibers in a configuration which corresponds to the areas of the final design which correspond to only one of the plurality of colors, i.e. color pattern, intended to be used in the final or overall design. In accordance with the present invention, each different color of flock is preferably applied sequentially using a

different screen to result in the particular precolored flock passing through the open section of the screen onto a corresponding section of the release adhesive 6 to form a color pattern.

5        Inasmuch as the precolored flock which form the color pattern do not require being printed with ink following flocking in order to effect different colors, as in a conventional multicolor transfer, the length of the flock can be as long as practical for the transfer depending on  
10 the desired aesthetic effect. In this regard, the flock fibers may be substantially longer than 0.3 mm, or even longer than 0.5-3 mm, the main limiting concern being the plushness of the texture of the flock transfer and the desired aesthetic effect which is intended to be achieved.  
15 In this regard, flock transfers having a fiber length of within the range of 3 mm up to 5 mm, and longer, can be used to result in a flock transfer which is much more plush, vivid and three dimensional than flock transfers wherein shorter fibers, i.e. 0.3 mm or 0.5-3 mm, are used. In  
20 accordance with the present invention, therefore, flock having a fiber length within the range of 5 mm to 1 cm is more preferred with a fiber length longer than 1 cm being most preferred.

Fig. 2 illustrates the application of the transfer to a  
25 textile 14, such as garment, or other surface. In accordance with the present invention, the substrate material, i.e., fabric or textile, can have a relatively smooth, regular surface, such as a piece of cloth, or may have a textured or irregular surface, such as fishnet  
30 material. In this regard, the present invention is applicable to any type of garment or piece of wearing apparel to which it is desired to affix or imprint a word, design, logo, emblem or other sign or symbol, particularly shirts, jerseys, jackets, pants, shorts and caps, such as  
35 those designed to be worn during athletic activities, e.g., U.S. football jerseys and baseball caps. Moreover, although

flock transfers are normally applied to substantially flat surfaces of a garment, the flock transfers of the present invention are particularly suitable for application of a flocked design to a curved or undulating surface without adversely affecting the vividness or other characteristics of the flocked design. Thus, the flock transfer of the present invention is advantageous in that it can be applied to almost any type of surface regardless of its texture or configuration. For example, although many textiles or fabrics to which flock designs are transferred may have a close-knit weave, the flock transfers of the present invention may be applied to fishnet and open mesh fabrics as well. To this end, the hot melt surface 12 is placed against the textile 14. Heat and pressure is applied to the release sheet 4 in order to bond the transfer to the garment. The release sheet 4 with the adhesive 6 is then pulled away from the flock 8. This leaves a transfer permanently affixed to the garment.

The present invention utilizes the general materials and flocking techniques found in the United States Patents 3,793,050; 4,292,100; and 4,396,662 and UK Patent applications 2,605,031 and 2,126,951, all of which are incorporated by reference herein.

Although the invention utilizes conventional materials and techniques which can be generally found in various prior art references, the specific manner by which the method of the present invention is performed permits a much longer flock than heretofore was practical to be used so that the particular combination of elements and the manner by which they are combined in accordance with the present invention produces a unique and superior flock transfer.

#### EXAMPLE

The following is an illustrative example of a method of producing the flock transfers for purposes of the invention comprises:

a) an acrylic layer 6 is applied in the reverse of a predetermined pattern to a dimensionally stable base sheet 4, such as a bond paper;

5 b) a first color of nylon flock fibers 8 having a length of about 5mm is passed through a monofilament polyester screen for ten to fifteen seconds in an electrostatic field. The screen has open sections in those areas which correspond to the first colored section of the reversed design. Inasmuch as the wax acts as a ground for  
10 the charged particles, the flock 8 becomes embedded in the wax layer 6;

c) this procedure is then followed for each succeeding color of nylon flock fibers 8 that is to be electrostatically flocked in order to form the desired  
15 design, after which the resultant unit is dried;

d) the tips of the exposed flock 8 are printed using conventional screen printing equipment with a water based (40%-60% water) acrylic binder 10. The binder 10 binds the flock 8 and further provides opacity and brilliance by  
20 reflecting light;

e) the binder 10 is dusted or powered with a polyurethane hot melt adhesive 12 and the transfer is then air-dried;

f) after brushing and vacuuming excess adhesive 12,  
25 the transfer is placed in an infrared dryer to cross link the binder 10 and adhesive 12 to form the multicolor flock transfer in accordance with the present invention.

To apply the transfer to a textile 14, the adhesive surface 12 is positioned on the textile 12. A hot surface  
30 heated to a temperature of about 300-350° F is pressed against the paper for about 20-30 seconds. The transfer is allowed to cool, preferably to an extent that it can be manipulated by hand, and the paper 4 and wax 6 are removed by peeling the paper 4 from the flock 8. The desired flock  
35 design is thus transferred and permanently affixed to the textile.

It is believed that the advantages and improved results furnished by the methods and products of the present invention are apparent from the foregoing description of the preferred embodiment of the invention. Various changes and  
5 modifications may be made without departing from the spirit and scope of the invention as described in the claims that follow.

DATED at PRETORIA on the 6th day of SEPTEMBER, 1988



J G SCHEFFLER  
PATENT ATTORNEY  
MACROBERT DE VILLIERS &  
HITGE INC

CLAIMS:

1. A method of making a multicolored flock transfer comprising:

5 a) printing a release adhesive upon a base sheet;

b) sequentially flocking different colored flock through an open section of a barrier into said adhesive to result in a plurality of predetermined single color patterns arranged to form a predetermined design; and

10 c) applying a binding adhesive to free ends of said flock.

2. The method of claim 1, wherein said base sheet is a material selected from the group consisting of paper, resin and metal foil.

15 3. The method of claim 2, wherein said base sheet is paper.

4. The method of claim 2, wherein said base sheet is transparent.

20 5. The method of claim 1 wherein said, colored flock comprise fiber having a length within the range of 3 mm to 5 mm.

6. The method of claim 1, wherein said colored flock comprises fibers having a length within the range of 5 mm to 1 cm.

25 7. The method of claim 1, wherein said colored flock comprises fibers have a length of at least about 1 cm.

8. The method of claim 1, wherein said different colored flock comprises fibers having a length longer than .3 mm.

30 9. The method of claim 1, wherein said barrier is a mesh screen.

10. The method of claim 1, wherein said binder adhesive is a resin.

35 11. The method of claim 10, wherein said resin is selected from the group consisting of polyvinyl chloride, polyvinyl acetate, polyurethane, polyester polyamide, and



acrylic resin.

12. The method of claim 1, wherein said binder adhesive is an acrylic resin.

13. the method of claim 1 wherein wherein said binding  
5 adhesive comprises a hot melt adhesive.

14. The method of claim 13, wherein said hot melt adhesive is selected from the group consisting of polyurethane, polyester and nylon.

15. The method of claim 14 further comprising applying  
10 a hot melt adhesive as a separate adhesive layer.

16. The method of claim 1, wherein said flock comprise conductive material.

17. The method of claim 16, wherein said conductive material is a synthetic material.

18. The method of claim 17, wherein said flock fibers  
15 comprise a material selected from the group consisting of acrylic rayon, nylon, polyamide and polyester materials.

19. The method of claim 18, wherein said material is nylon.

20. A multicolor flock transfer comprising:  
20

a) a base sheet having a surface area coated with a release adhesive;

b) precolored flock of at least two different colors having ends adhering to said surface area to form  
25 predetermined color patterns of a design; and

c) a binding adhesive applied to other ends of said precolored flock.

21. The multicolor flock transfer of claim 20, wherein said precolored flock comprises fibers having a length  
30 greater than 0.3 mm.

22. The multicolor flock transfer of claim 21, wherein said length is within the range of 0.5 mm to 3 mm.

23. The multicolor flock transfer of claim 21, wherein said length is within the range of 3 mm to 5 mm

24. The multicolor flock transfer of claim 23, wherein  
35 said length within the range of 5 mm to 1 cm.

25. The multicolor flock transfer of claim 21, wherein said length is longer than 1 cm.

26. The multicolor flock transfer of claim 21, wherein said flock comprise conductive material.

5 27. The multicolor flock transfer of claim 26, wherein said conductive material is a synthetic material.

28. The multicolor flock transfer of claim 27, wherein said synthetic material is selected from the group consisting of acrylic, rayon, nylon, polyester and  
10 polyamide.

29. The multicolor flock transfer of claim 28, wherein said flock comprise rayon.

30. The multicolor flock transfer of claim 26, wherein said base sheet is selected from the group consisting of  
15 paper, resin and metal foil.

31. The multicolor flock transfer of claim 30, wherein said sheet is paper.

32. The multicolor flock transfer of claim 30, wherein said release adhesive is selected from member of the group  
20 consisting of silicone wax, polyvinyl acetate, polyvinyl alcohol, polyvinyl chloride, polyvinyl butyral, acrylic resin, polyurethane, polyester, polyamides, cellulose derivatives, rubber derivatives, starch, casein, dextrin, gum arabic, carboxymethyl cellulose, resin and mixtures of  
25 at least two of said members.

33. The multicolor flock transfer of claim 32, wherein said release adhesive is silicone wax.

34. The multicolor flock transfer of claim 32, wherein said binding additive comprises a resin.

30 35. The multicolor flock transfer of claim 34, wherein said resin is selected from the group consisting of polyvinyl chloride, polyvinyl acetate, polyurethane, polyester, polyamide, and acrylic resin.

36. The multicolor flock transfer of claim 35, wherein  
35 said resin is an acrylic resin.

37. The multicolor flock transfer of claim 36, wherein

said acrylic resin is a water-based acrylic.

38. The multicolor flock transfer of claim 34, wherein said binder adhesive comprises a supplemental adhesive selected from the group consisting of hot melt adhesives.

5 39. The multicolor flock transfer of claim 38, wherein said hot melt adhesive is selected from the group consisting of polyurethane, polyester and nylon.

40. The multicolor flock transfer of claim 20, further comprising:

10 d) a layer of supplemental adhesive covering said binding adhesive.

41. The multicolor flock transfer of claim 40, wherein said supplemental adhesive is selected from the group consisting of polyurethane, polyester, nylon, polyamide, 15 polyethylene, thermoplastic acrylic resin, polyvinyl chloride, paraffin and rubber derivatives.

42. The multicolor flock transfer of claim 41, wherein said supplemental adhesive is selected from the group consisting of polyurethane, polyester and nylon.

20 43. A process for manufacturing transfer sheets comprising:

forming on the surface of a base sheet an adhesive layer for temporary adhesion of a plurality of different colored flock fibers to the base sheet, temporarily sticking 25 said different colored flock to said adhesive layer to form a multicolored fiber layer, and applying an adhesive in said multicolor fiber layer to a desired pattern to form a binding adhesive layer, wherein said colored flock are precolored to said plurality of different colors before 30 sticking said different colored flock fibers to said adhesive layer.

44. The process for manufacturing multicolor transfer sheet in accordance with claim 43, wherein said colored flock comprises fibers having a length within the range of 3 35 mm to 5 mm.

45. The multicolor flock transfer of claim 44, wherein

said length is within the range of 5 mm to 1 cm.

46. A multicolored flock transfer comprising precolored flock including fibers having a length longer than about 3 mm.

5 47. The multicolor flock transfer wherein said length is within the range of about 3 mm to 5 mm.

48. The multicolor flock transfer of claim 46, wherein said length is within the range of 5 mm to 1 cm.

49. The multicolor flock transfer of claim 46 wherein  
10 said length is longer than 1 cm.

50. A fabric comprising:

a) a substrate material;

b) a layer of binding adhesive having a predetermined design applied to said substrate; and

15 c) precolored flock of at least two different colors adhering to said layer.

51. The fabric of claim 50, wherein said flock comprises fibers having a length longer than about 3 mm.

52. The fabric of claim 51, wherein said length is  
20 within the range of about 3 mm to about 5 mm.

53. The fabric of claim 51 wherein said length is within the range of about 5 mm to about 1 cm.

54. The fabric of claim 51 wherein said length is longer than about 1 cm.

25 55. A method of applying a flocked design onto a product comprising:

a) printing a release adhesive on a plurality of base sheets;

30 b) flocking with different precolored flocks into said adhesive to form a plurality of color patterns into said predetermined design in said adhesive;

c) applying a binding adhesive to free ends of said precolored flocks to form flock transfer sheets; and

35 d) transferring said precolored flock from one of said flock transfer sheets onto a substrate material to vividly form said flock in said predetermined design on said

substrate material thereby producing a product having a flocked design.

56. The method of claim 55, wherein said flocks comprise fibers having a length longer than 3 mm.

5 57. The method of claim 56, wherein said length is within the range of about 3 mm - 5 mm.

58. The method of claim 56, wherein said length is within the range of 5 mm - 1 cm.

59. The method of claim 56, wherein said length is  
10 longer than 1 cm.

FIBERLOK INC

1 SHEET  
SHEET NO 1

88/6259




FIG. 1





FIG. 2

MACROBERT DE VILLIERS & HITGE INC

  
JG SCHEFFLER  
PATENT ATTORNEY